

Description

Anodized 6063 T5 aluminum alloy profile with a thickness of 0.9 mm / 0.035" that protects coating joints. Thin and simple design.



Profile

h 10 mm / 3/8" 2.5 mm / 3/32" 1 2 mm / 1/2" 2.5 mm / 3/32" 2.50 m / 98"	w		h:	w:	Longth
h 12 mm / 1/2" 2.5 mm / 3/32" 2.50 m / 98"		h	10 mm / 3/8"	2.5 mm / 3/32"	Length:
			12 mm / 1/2"	2.5 mm / 3/32"	2.50 m / 98"
15 mm / 19/32" 2.5 mm / 3/32"		↓	15 mm / 19/32"	2.5 mm / 3/32"	

Check availability of other sizes in your country.

Uses and applications

It enables the joint of two coatings at a 90° angle and can be used as corner post, decorative lath or wall finish.

Uses: interior walls.



Advantages

• In addition to decorating the joint between two planes, it protects the edge of ceramic tiles and porcelain tiles avoiding damages and scratches.

Argentina 0810-22-ATRIM (28746) ventasatrim@atrimglobal.com Chile +56 2 3210 3817 ventas@atrimglobal.com Colombia +57 601 508 4846 ventas@atrimglobal.com Mercosur +54 11 2821 8900 ventas@atrimglobal.com **Centroamérica / Caribe** +57 316 4405239 ventas@atrimglobal.com

1/2



Material properties

ANODIZED ALUMINUM: Anodizing is the name given to the electrolytic passivation process used to increase the thickness of the natural oxide layer on the surface of metal parts. This technique is usually used on aluminum to create an artificial shield layer through the oxide that protects the aluminum, known as alumina. The layer is obtained through electrochemical processes that provide higher resistance and durability of the aluminum.

Installation method

- 1. Choose the profile according to the coating height.
- 2. Apply adhesive with a notched trowel on one of the walls.
- 3. Complete the coating installation on the lateral wall.
- **4.** Place the L-shaped rod on the corner, aligning the drilled "A"-shaped hitch leg.
- 5. Press the profile on the wall until the adhesive sticks out of the perforations.
- 6. Place the adjacent ceramic tiles at the same level as the profile.
- 7. Install the coating with crosshead spacers to guarantee an even joint that must later be filled with grout or forge.
- 8. Clean the rod with a damp cloth to prevent the glue from drying on them.



Cleaning and maintenance

Clean the aluminum profiles with a soft cloth regularly. When using a neutral cleaner, it must be diluted with cold water and then dried to remove the damp effect. If damp persists, clean it with a 5% solution of detergent or neutral soap in clear water and wipe with a cloth that does not contain particles to avoid scratching.

It is not advisable to use:

- Steel wool since it could scratch the surface.
- Hydrochloric acid or iron products in prolonged contact.
- Materials that contain chlorides.
- Setting accelerators that contain chlorides.
- Carbon steel cleaners for stainless steel.



How to install the arch edge guard for walls video www.youtube/atrimglobal

Argentina 0810-22-ATRIM (28746) ventasatrim@atrimglobal.com Chile +56 2 3210 3817 ventas@atrimglobal.com Colombia +57 601 508 4846 ventas@atrimglobal.com Mercosur +54 11 2821 8900 ventas@atrimglobal.com Centroamérica / Caribe +57 316 4405239 ventas@atrimglobal.com

2/2